

Chemical Analysis	
SiO₂	48.0%
Al₂O₃	36.0%
K₂O	2.10%
Fe₂O₃	1.30%
TiO₂	0.05%
CaO	0.01%
Na₂O	0.01%
MgO	0.01%
LOI	12.5%

Fired Properties at 1250°C	
Whiteness, L*	92.0%
Dry to fired Shrinkage (wt%)	7.0%
Water absorption	17.0%